



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>7</sup> :</b> <b>C07D 127/12, C08J 7/64, 7/27, C08F 214/18</b>	<b>A2</b>	<b>(11) International Publication Number:</b> <b>WO 00/55130</b> <b>(43) International Publication Date:</b> 21 September 2000 (21.09.00)
<b>(21) International Application Number:</b> PCT/US00/07263 <b>(22) International Filing Date:</b> 15 March 2000 (15.03.00)  <b>(30) Priority Data:</b> 60/124,520 16 March 1999 (16.03.99) US  <b>(71) Applicant (for all designated States except US):</b> E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US).  <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> FEIRING, Andrew, Edward [US/US]; 7 Buckridge Drive, Wilmington, DE 19807 (US). IWATO, Satoko [JP/JP]; 4-27-8, Jingumae, Shibuya-ku, Tokyo (JP). KAKU, Mureo [JP/JP]; 2-32-2, Toyosatodai Utsunomiya, Tochigi (JP). TATSUHIRO, Takahasi [JP/JP]; Pepaminto Haitzu A27, 1-3-2 Matsugasaki, Yonezawa-shi, Yamagata (JP). USCHOLD, Ronald, Earl [US/US]; 1104 Dorset Drive, West Chester, PA 19382 (US). WHELAND, Robert, Clayton [US/US]; 510 Twaddell Mill Road, Wilmington, DE 19807 (US).  <b>(74) Agent:</b> SIEGELL, Barbara, C.; E.I. du Pont de Nemours and Company, Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).		<b>(81) Designated States:</b> CA, JP, KR, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> <i>Without international search report and to be republished upon receipt of that report.</i>
<b>(54) Title:</b> FLUOROPOLYMER LOW REFLECTING LAYERS FOR PLASTIC LENSES AND DEVICES  <b>(57) Abstract</b> <p>A one or two layer coating system has been developed for plastic substrates. The one coating system low reflecting layer consists of VF<sub>2</sub>/TFE/HFP. In the two coating system is the upper coating layer consists of TFE/HFP, VF<sub>2</sub>/TFE/HFP, or TFE/Perfluorodioxole, and the lower coating layer consists of VF<sub>2</sub>/TFE/HFP, VF/TFE/HFP, VAc/TFE/HFIB, or TFE graft to PVOH. A new fluoropolymer composition was prepared for use in the coating systems, prepared by the copolymerization of vinyl acetate, tetrafluoroethylene, and hexafluoroisobutylene.</p>		

*FOR THE PURPOSES OF INFORMATION ONLY*

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

TITLEFLUOROPOLYMER LOW REFLECTING LAYERS  
FOR PLASTIC LENSES AND DEVICESFIELD OF INVENTION

5       The present invention relates to fluoropolymer coated plastics. More specifically, it relates to fluoropolymer coated plastics having good adhesion, low reflective properties, and water and oil repellency.

TECHNICAL BACKGROUND

10       Much work has been done concerning low reflective plastics, particularly for plastic lenses and optical devices. One method used is vapor disposition of oxidized metal on the surface of the plastic. However, this method uses a batch process and when the substrate is large, the productivity becomes low. Another way is to apply a coating of fluoropolymer solutions. The coating is done by a dipping process and is applicable for large substrates with high productivity.

15       Though fluoropolymers have low reflective indexes, they also have very poor adhesion with plastic substrates. Improvement in the adhesion between fluoropolymers and substrate plastics has been long sought. The purpose of this invention is to provide the technology for low reflective index and good adhesion using fluoropolymer solutions.

20       SUMMARY OF THE INVENTION

The one layer coating system provided by the present invention consists of a fluorinated copolymer having the formula



25       wherein the molar ratio of Tetrafluoroethylene (TFE) to Hexafluoropropylene (HFP) is between 0.3 and 1.9, and the VF<sub>2</sub> content is preferably 12 to 50 mole % for PMMA substrates and 18 to 50 mole % for PC, PET, and PS substrates. More preferred is where the molar ratio of TFE to HFP is between 0.9 and 1.9, and the

30       VF<sub>2</sub> content is preferably 12 to 40 mole % for Polymethylmethacrylate (PMMA) substrates and 18 to 40 mole % for Polycarbonate (PC), Polyethyleneterephthalate (PET), and Polysulfone (PS) substrates.

In the case of the present invention the two-layer coating system developed for PMMA, PC, PET, and PS substrates comprises an upper layer

35       selected from the group consisting of:

a) poly(TFE/HFP) and poly(VF<sub>2</sub>/TFE/HFP), wherein the molar ratio of HFP to TFE is between about 0.3 and 1.9 and, in the case of the VF<sub>2</sub>/TFE/HFP terpolymer, the concentration of VF<sub>2</sub> is about 19 mole %; and

b) poly(TFE/perfluoro-2,2-dimethyldioxole) wherein the concentration of the perfluorodimethyldioxole is between 60 and 90 mole %; and a lower coating layer selected from the group consisting of:

5 a) poly(VF<sub>2</sub>/TFE/HFP) wherein the ratio of TFE to HFP is between about 0.3 and 1.9 and the concentration of VF<sub>2</sub> is between about 18 and 60% on PMMA substrates and between about 12 and 40 mole % on PC, PET, and PS substrates;

10 b) poly(VF/TFE/HFP) wherein the ratio of TFE to HFP is between about 2.1 and 0.9 and the concentration of VF is between about 42 and 58 mole %;

c) poly(VAc/TFE/HFIB) wherein the concentration of VAc is between 36 and 69 mole % and the concentration of HFIB is between 14 and 52 mole %; and

15 d) TFE graft to PVOH wherein about 46 mole % TFE has been grafted to the PVOH.

More preferred is where the ratio of TFE to HFP is between about 0.9 and 1.9 in both the lower and upper layer, and wherein the concentration of VF<sub>2</sub> is between about 12 and 40 mole % when PC, PET, and PS substrates are utilized.

20 In the one layer coating system of the present invention, the thickness of the coating is preferably between about 10 and 1000 nm, more preferably, between about 30 and 120 nm, and most preferably between about 70 and 120 nm.

In the two coat system, the thickness of the upper layer is preferably between 10 and 1000 nm. More preferably, it is between 30 and 120 nm and 25 most preferably, it is between 70 and 120 nm.

Another aspect of the invention is a new fluoropolymer composition prepared by the polymerization of vinyl acetate (VAc, CH<sub>3</sub>-C(O)-OCH=CH<sub>2</sub>), tetrafluoroethylene (TFE, CF<sub>2</sub>=CF<sub>2</sub>), and hexafluoroisobutylene (HFIB, (CF<sub>3</sub>)<sub>2</sub>C=CH<sub>2</sub>).

### 30 DETAILED DESCRIPTION OF THE INVENTION

Both one layer and two layer systems have been found that afford low reflection coatings on optically clear plastic substrates. Preferred substrates are PMMA, PC, PET, and PS.

35 The one layer coating system provided by the present invention consists of a fluorinated copolymer having the formula



wherein the molar ratio of TFE to HFP is between 0.3 and 1.9 and the VF<sub>2</sub> content is preferably 12 to 50 mole % for PMMA substrates and 18 to 50 mole % for PC, PET, and PS substrates. These compositions balance the high fluorine content needed for low reflection, the high HFP content needed for optical clarity, and a sufficient VF<sub>2</sub> content to afford good adhesion to the substrate. More preferred is where the molar ratio of TFE to HFP is between 0.9 and 1.9, and the VF<sub>2</sub> content is preferably 12 to 40 mole % for PMMA substrates and 18 to 40 mole % for PC, PET, and PS substrates.

Although many polymers have a high enough fluorine content to perform well as a low reflection coating, they often fail because of inadequate bonding to substrates such as PMMA, PC, PET, and PS. This adhesion problem has been solved by going to systems in which a lower adhesive coat bonds a low-reflective top coat to the substrate. In the case of the present invention the two-layer coating system developed for PMMA, PC, PET, and PS substrates consists of fluoropolymers having the formulas

Upper coating layer:

Poly(TFE/HFP) and poly(VF<sub>2</sub>/TFE/HFP), wherein the molar ratio of HFP to TFE is between about 0.3 and 1.9 and, in the case of the VF<sub>2</sub>/TFE/HFP terpolymer, the concentration of VF<sub>2</sub> is about 19 mole %

or

poly(TFE/perfluoro-2,2-dimethyldioxole) wherein the concentration of the perfluorodimethyldioxole is between 60 and 90 mole %

Lower coating layer:

Poly(VF<sub>2</sub>/TFE/HFP) wherein the ratio of TFE to HFP is between about 0.3 and 1.9 and the concentration of VF<sub>2</sub> is between about 18 and 60% on PMMA substrates and between about 12 and 50 mole % on PC, PET, and PS substrates

or

Poly(VF/TFE/HFP) wherein the ratio of TFE to HFP is between about 2.1 and 0.9 and the concentration of VF is between about 42 and 58 mole %

or

Poly(VAc/TFE/HFIB) wherein the concentration of VAc is between 36 and 69 mole % and the concentration of HFIB is between 14 and 52 mole %

or

A TFE graft to PVOH wherein about 46 mole % TFE has been grafted.

More preferred is where the ratio of TFE to HFP is between about 0.9 and 1.9 in both the lower and upper layer, and wherein the concentration of  $\text{VF}_2$  is between about 12 and 40 mole % when PC, PET, and PS substrates are utilized.

The purpose of the lower layer in the present invention is to bond highly-  
5 fluorinated, low-reflection polymers to higher-reflection, hydrocarbon-polymer substrates. In order to be an effective adhesive agent, the polymer used for the adhesive layer combines perfluorocarbon monomers such as TFE and HFP with either partially fluorinated or hydrocarbon comonomers such as  $\text{VF}_2$ , HFIB, and VAc.

10 In the one layer coating system of the present invention, the coating needs to be thicker than about 10 nm in order to observe a significant reduction in reflectivity. While thicknesses greater than 10 nm work well, practical problems eventually arise as the coating is made thicker. For example, above about 1000 nm, thickness variation can become a problem, and, if the coating polymer  
15 is expensive, economics start to be prohibitive. Thus, in the one layer coating system of the present invention, the thickness of the coating is preferably between about 10 and 1000 nm, more preferably, between about 300 and 120 nm, most preferably, between about 70 and 120 nm.

In the two layer coating system of the present invention the thickness of  
20 the upper layer can be between 10 and 1000 nm. More preferably, it is between about 30 and 120 nm, most preferably between about 70 and 120 nm. The coating process for the present invention can include any process known in the art, including but not limited to dipping, spray, or spin coating method using polymer.

25 Another aspect of the invention is a new fluoropolymer composition prepared by the copolymerization of vinyl acetate (VAc,  $\text{CH}_3\text{-C}(\text{O})\text{-OCH=CH}_2$ ), tetrafluoroethylene (TFE,  $\text{CF}_2=\text{CF}_2$ ), and hexafluoroisobutylene (HFIB,  $(\text{CF}_3)_2\text{C=CH}_2$ ). The polymer can be produced using any free-radical polymerization method known in the art, including but not limited to bulk,  
30 solution or dispersion polymerization, using either nonaqueous or aqueous solvents. A preferred method is dispersion polymerization. Preferred solvents are water and tert-butanol/methyl acetate mixture. Dispersing agents can optionally be used; a preferred initiator is Vazo<sup>®</sup>52. The polymer can further be hydrolyzed, partially or completely, to provide a vinyl alcohol containing  
35 copolymer.

The polymer can be recovered from the reaction using any conventional procedure such as filtration, followed by washing and drying. The polymer product can be readily dissolved in many solvents such as acetone and used for

casting films and surface coatings having the advantageous properties of fluoropolymers. One particular use is for preparing coatings having low reflective properties.

The following non-limiting Examples are meant to illustrate the invention  
5 but are not intended to limit it in any way.

#### Materials and Methods

The following definitions are used herein and should be referred to for claim interpretation.

- APS – Ammonium persulfate
- 10 HFIB – Hexafluoroisobutylene,  $(\text{CF}_3)_2\text{C}=\text{CH}_2$
- HFP – Hexafluoropropylene,  $\text{CF}_2=\text{CF}-\text{CF}_3$
- PC - Polycarbonate
- PET – Polyethyleneterephthalate
- PMMA - Polymethylmethacrylate
- 15 PVOH – Polyvinyl alcohol
- PS - Polysulfone
- Teflon<sup>®</sup> AF - TFE/Perfluoro-2,2-dimethyldioxole copolymer
- TFE – Tetrafluoroethylene,  $\text{CF}_2=\text{CF}_2$
- VAc – Vinyl acetate,  $\text{CH}_3-\text{C}(\text{O})-\text{OCH}=\text{CH}_2$
- 20 VF – Vinyl fluoride,  $\text{CH}_2=\text{CHF}$
- VF<sub>2</sub> – Vinylidene fluoride,  $\text{CF}_2=\text{CH}_2$

Unless otherwise indicated, the following test methods were used:

#### Method of measuring transmission

Light transmission was measured at 500 nm using a Shimadzu #UV-3100  
25 Spectrometer. This machine measures a continuous comparison of a split beam, part of which passes through the sample.

#### Adhesion Test Method

A tool with 10 razor blades separated by a distance of 1 mm was used to cut the coating down to the plastic substrate, drawing the razor blade tool first in  
30 one direction and then a second time in a perpendicular direction. This cuts 100 crosshatched squares. Scotch tape was applied to the crosshatched area with moderate pressure and pulled off rapidly. Adhesion is scored as the number of squares out of 100 still attached to the substrate.

Unless otherwise indicated, all other polymers and monomers were  
35 obtained are commercially available.

The VF<sub>2</sub>/TFE/HFP terpolymers and the TFE/HFP dipolymers used in the present invention are compositions chosen for optical clarity and solubility. They were prepared by polymerization at 14,000 psi and 200-400°C as described in

U.S. Patent Nos. 5,478,905 and 5,637,663. This method of polymerization gives higher HFP contents and different monomer sequences than polymerizations run under ordinary emulsion and bulk polymerization methods known in the art, see for instance, *Encyclopedia of Polymer Science and Engineering*, 1989. Vol. 16, pg 601-613 and Vol. 7, pg. 257-269, John Wiley & Sons. VF<sub>2</sub>/TFE/HFP and TFE/HFP copolymers made by these more conventional methods may also work in our application as long as high fluorine content, optical clarity and easy solution coatability can be maintained.

PVOH grafted with TFE was prepared as in U.S. Patent No. 5,847,048, hereby incorporated by reference. The polymer contained about 46 mole % TFE groups grafted to the vinyl alcohol.

The VAc/TFE/HFIB terpolymers were prepared as described in Examples 36 to 45 below.

### EXAMPLES

#### EXAMPLES 1-9

#### COMPARATIVE EXAMPLES 1-3

#### One Coat Poly(VF<sub>2</sub>/TFE/HFP) on PMMA

#### Preferred Thickness Range

Solutions, 2 wt % poly(VF<sub>2</sub>/TFE/HFP) in Fluorinert® FC-75, were made by agitating chunks of the polymer with solvent for several days at room temperature. PMMA plates measuring 2.5 cm by 5.0 cm by 3 mm thick were used for testing. The PMMA plates were coated by lowering the plates into the polymer solution at a rate of 300 mm/min. and then, 30 seconds later, raising the plates back out of the solution at 2.5 to 1000 mm/min. After 5-10 minutes air drying, the plates were dried horizontally for 60 minutes in a 100°C air oven. Examples are in order of increasing coating thickness.

TABLE 1

Single Coat of 18.7/43.3/38.0 mole % Poly(VF<sub>2</sub>/TFE/HFP) on PMMA

	<u>Thickness (nm)</u>	<u>Transmittance (%)</u>
Comp. #1	Uncoated PMMA control	92.1
Comp. #2	5.0	92.8
Example #1	20.0	94.5
Example #2	70.6	96.7
Example #3	76.3	97.7
Example #4	90.2	98.0
Example #5	106.2	96.6
Example #6	133.3	93.2
Example #7	209.2	94.6



Example #8	394.7	95.2
Example #9	572.1	94.4
Comp. #3	2000	not uniform

Uncoated PMMA showed 92.1% transmission. Coatings thicker than 20.0 nm and thinner than 1000 nm gave improved transmission (>93%) relative to uncoated PMMA. The highest transmissions (>96%) were shown by coatings  
 5 ~30 to 120 nm thick.

#### EXAMPLES 10-13

#### COMPARATIVE EXAMPLES 4-5

One Coat Poly(VF<sub>2</sub>/TFE/HFP) on PMMA

Preferred VF<sub>2</sub> Content

10 Polymer films were prepared as in Examples 1 to 9. Transmittance and adhesion were measured with the results shown in Table 2 below which lists Examples and Comparative Examples in order of increasing VF<sub>2</sub> content.

TABLE 2

Adhesion by Standard Tape Pull Test  
 Single Coat Poly(VF<sub>2</sub>/TFE/HFP) on PMMA

	Mole % VF <sub>2</sub> /TFE/HFP	Adhesion (/100)	Transmittance (%)
Comp. #1	Uncoated PMMA control	--	92.1
Comp. #4	0/57/43 Control	0	97.2
Comp. #5	7.8 /60.3/31.8	64	97.5
Example #10	12.6/51.3/36.1	96	97.2
Example #11	18.7/43.3/18.0	99	97.9
Example #12	25.2/42.9/31.9	100	95.1
Example #13	37.4/28.9/33.7	100	96.0

15 Simultaneous good adhesion (>96/100) and improved transmission (>97%) relative to uncoated PMMA were observed for VF<sub>2</sub>/TFE/HFP polymers with 12 to 50 mole % VF<sub>2</sub>.

#### EXAMPLE 14

A solution, 2 wt % poly(VF<sub>2</sub>/TFE/HFP = 46.9/13.5/39.6 mole %) in  
 20 Vertrel<sup>®</sup> XF, were made by agitating chunks of the polymer with solvent for several days at room temperature. PMMA plates measuring 2.5 cm by 5.0 cm by 3 mm thick were used for testing. The PMMA plates were coated by lowering the plates into the polymer solution at a rate of 300 mm/min. and then, 30 seconds later, raising the plates back out of the solution at 50 mm/min. After  
 25 5-10 minutes air drying, the plates were dried horizontally for 60 minutes in a

100°C air oven. Transmittance and adhesion were measured with the results shown the table below which lists Examples.

TABLE 3

Single Coat of 46.9/13.5/39.6 mole % Poly(VF<sub>2</sub>/TFE/HFP) on PMMA

	Mole %'s VF <sub>2</sub> /TFE/HFP	Adhesion (/100)	Transmittance (%)
Example #14B	46.9/13.5/39.6	100	97.4
Comp. #1	Uncoated PMMA control	--	92.1

- 5 Simultaneous good adhesion (100/100) and improved transmission (>97%) relative to uncoated PMMA were observed for VF<sub>2</sub>/TFE/HFP = 46.9/13.5/39.6 mole % terpolymer.

EXAMPLES 15-18

COMPARATIVE EXAMPLES 6-8

- 10 Two Coats, Poly(VF<sub>2</sub>/TFE/HFP) and Poly(HFP/TFE), on PMMA  
Preferred VF<sub>2</sub> Content

- Solutions, 1 wt % poly(VF<sub>2</sub>/TFE/HFP) with 0-40% VF<sub>2</sub> in Fluorinert<sup>®</sup> FC-75, and with 4-55 mole % VF<sub>2</sub> in acetone were made by agitating chunks of the polymer with solvent for several days at room temperature. PMMA plates measuring 2.5 cm by 5.0 cm by 3 mm thick were used for testing. The PMMA plates were coated by lowering the plates into the polymer solution at a rate of 300 mm/min. and then, 30 seconds later, raising the plates back out of the solution at 50 mm/min. After 5-10 minutes air drying, the plates were dried horizontally for 60 minutes in a 100°C air oven. Examples and Comparative Examples are listed in order of increasing.

- 20 VF<sub>2</sub> content in the poly(VF<sub>2</sub>/TFE/HFP) primer coat was varied. A 57 mole % TFE/43 mole % HFP top coat was used for all samples with a poly(VF<sub>2</sub>/TFE/HFP) primer coat. Transmittance and adhesion were measured with the results shown in Table 4 below which lists the Examples and Comparative Examples in order of increasing thickness.

TABLE 4

Two Coat, Poly(VF<sub>2</sub>/TFE/HFP) and Poly(HFP/TFE) on PMMA  
Preferred VF<sub>2</sub> Content

	Mole % VF <sub>2</sub> /TFE/HFP	Adhesion (/100)	Transmittance (%)
Comp. #1	Uncoated PMMA control	--	92.1
Comp. #4	0/57/43 Control	0	97.2
Comp. #6	7.8 /60.3/31.8	0	97.7
Comp. #7	12.6/51.3/36.1	4	97.5
Example #15	18.7/43.3/38.0	90	97.7
Example #16	49.3/27.7/23.0	100	97.3
Example #17	52.0/25.9/22.1	98	97.5
Example #18	61.0/21.7/17.3	80	97.4
Comp. #8	66.2/16.9/16.9	6	97.1

Good adhesion with increased transmission relative to uncoated PMMA control was observed when the poly(VF<sub>2</sub>/TFE/HFP) primer layer had VF<sub>2</sub> contents between about 18 and 60 mole.

EXAMPLES 19-21

Two Coats both Poly(VF<sub>2</sub>/TFE/HFP) on PMMA

Transmittance Independent of VF<sub>2</sub> Content of Primer Coat

Poly(VF<sub>2</sub>/TFE/HFP) samples of different VF<sub>2</sub> content, see Table 5 below, were used for the primer coat. Solutions, 1 wt % poly(VF<sub>2</sub>/TFE/HFP) in acetone, were made by agitating chunks of the polymer with solvent for several days at room temperature. PMMA plates measuring 2.5 cm by 5.0 cm by 3 mm thick were used for testing. The PMMA plates were coated by lowering the plates into the polymer solution at a rate of 300 mm/min. and then, immediately, raising the plates back out of the solution at 50 mm/min. After 5-10 minutes air drying, the plates were dried horizontally for 60 minutes in a 100°C air oven. The topcoat, in every instance the same 18.7 mole % VF<sub>2</sub>/43.3 mole % TFE/38.0 mole % HFP terpolymer, was prepared by the same method.

Table 5 below lists Examples and Comparative Examples in order of increasing VF<sub>2</sub> content.

TABLE 5  
Two Poly(VF<sub>2</sub>/TFE/HFP) Coats on PMMA

	Primer Coat Mole % VF <sub>2</sub> /TFE/HFP	Adhesion (/100)	Transmittance (%)
Comp. #1	Uncoated PMMA Control	---	92.1
Example 19	49.3/27.7/23.0	100	97.5
Example 20	61.0/21.7/17.3	100	97.0
Example 21	66.2/16.9/16.9	100	97.5

In spite of variation in VF<sub>2</sub> content from 49.3 to 66.2 mole % in the lower layer, overall transmittance is relatively unaffected. Adhesion is excellent (100/100) for VF<sub>2</sub> contents from 49.3 to 66.2 mole %.

EXAMPLES 22 TO 24

COMPARATIVE EXAMPLES 9-12

One Coat Poly(VF<sub>2</sub>/TFE/HFP) on Polycarbonate

Preferred VF<sub>2</sub> Content

Poly(VF<sub>2</sub>/TFE/HFP) terpolymer samples of different VF<sub>2</sub> content were coated on polycarbonate (PC) sheet using the method of Example 14. The polycarbonate was manufactured by Kyoto-Jushi Seiko Co., Ltd. The polycarbonate sheets measured 2.5 cm X 5.0 cm by 3 mm thick.

Transmission and adhesion were measured with the results shown in Table 6 below which lists Examples and Comparative Examples in order of increasing VF<sub>2</sub> content.

TABLE 6  
Single Poly(VF<sub>2</sub>/TFE/HFP) Coat on PC

	Mole %'s VF <sub>2</sub> /TFE/HFP	Adhesion (/100)	Transmittance (%)
Comp. #9	Uncoated PC Control	--	87.2
Comp. #10	0/57/43	0	95.2
Comp. #11	7.8/60.3/31.8	0	90.5
Comp. #12	12.6/51.3/36.1	53	94.7
Example #22	18.7/43.3/38.0	70	94.0
Example #23	25.2/42.9/31.9	100	92.0
Example #24	37.4/28.9/33.7	100	93.8

VF<sub>2</sub> contents between about 18 and 40 mole % give improved adhesion (>70/100) relative to HFP/TFE copolymer (0/100) and improved transmission (>92%) relative to uncoated PC (87.2%).

EXAMPLES 25-28COMPARATIVE EXAMPLES 13 TO 14

## Two Coats on Polycarbonate

Preferred VF<sub>2</sub> Content for Primer

5 Poly(VF<sub>2</sub>/TFE/HFP) samples of different VF<sub>2</sub> content, see Table 7 below, were used for the primer coat. Solutions, 1 wt % poly(VF<sub>2</sub>/TFE/HFP) in acetone, were made by agitating chunks of the polymer with solvent for several days at room temperature. PC plates (Kyoto-Jushi Seiko Co., Ltd.) measuring 2.5 cm by 5.0 cm by 3 mm thick were used for testing. The PC plates were coated by  
 10 lowering the plates into the polymer solution at a rate of 300 mm/min. and then, immediately, raising the plates back out of the solution at 50 mm/min. After 5-10 minutes air drying, the plates were dried horizontally for 60 minutes in a 100°C air oven.

The topcoat, in every instance the same 57.0 mole % TFE/43.0 mole %  
 15 HFP copolymer, was prepared by the same method.

Table 7 below lists Examples and Comparative Examples in order of increasing VF<sub>2</sub> content.

TABLE 7

## Two Coats on PC

	Primer Coat Mole % VF <sub>2</sub> /TFE/HFP	Adhesion (/100)	Transmittance (%)
Comp. #9	Uncoated PC control	--	87.2
Comp. #13	0/57/43 control	68	93.8
Comp. #14	7.8/60.3/31.8	12	91.6
Example #25	12.6/51.3/36.1	83	94.2
Example #26	18.7/43.3/38.0	96	92.3
Example #27	25.2/42.9/31.9	88	93.4
Example #28	37.4/28.9/33.7	97	93.2

20 VF<sub>2</sub> contents between about 12 and 40 mole % give improved adhesion (>83/100) relative to HFP/TFE dipolymer (68/100) and improved transmittance (>92.3%) relative to uncoated polycarbonate (87.2%).

EXAMPLES 29 TO 31

## Two Coats on PMMA

25 Use of Poly(VF/TFE/HFP) as Primer Coat

## Preferred VF Content

A stirred jacketed stainless steel horizontal autoclave of 7.6 L (2 U.S. gal) capacity was used as the polymerization vessel. The autoclave was equipped with

instrumentation to measure temperature and pressure and with a compressor that could feed monomer mixtures to the autoclave at the desired pressure. The autoclave was filled to 55-60% of its volume with deionized water containing 15 g of Zonyl<sup>®</sup> FS-62 surfactant (DuPont Co., Wilmington, DE) and heated to 90°C. It was then pressured to 3.1 MPa (450 psig) with nitrogen and vented three times. The autoclave was precharged with monomers in the desired ratio, as shown in the table below, and brought to the working pressure of 3.1 MPa (450 psig). Initiator solution was prepared by dissolving 2 g APS in 1 L of deionized water. The initiator solution was fed to the reactor at a rate of 25 mL/min for a period of five minutes and then the rate was reduced and maintained at 1 mL/min for the duration of the experiment. For Examples 36 and 38 the autoclave was operated in a batch mode. The polymerization was terminated after a 10% pressure drop was observed by venting the remaining unconverted monomers and by reducing the autoclave temperature to room temperature.

For the 26.2/46.4/27.5 polymer, the autoclave was operated in a semibatch fashion in which a monomer mixture was added to the reactor to maintain constant pressure by means of the compressor as polymerization occurred. The composition of this make-up feed was different from the precharged mixture, as shown in the table below, because of the differences in monomer reactivity. The composition was selected to maintain a constant monomer composition in the reactor so compositionally homogeneous product was formed. Make-up monomer feed was admitted to the autoclave, through the compressor, by means of an automatic pressure regulated valve to maintain reactor pressure. Monomer feeds were continued until a predetermined amount to give the final latex solids was fed to the autoclave. The feed was then stopped and the contents of the autoclave were cooled and vented.

In all cases, the polymer latex was easily discharged to a receiver as a milky homogeneous mixture. Polymer was isolated on a suction filter after adding 15 g of ammonium carbonate dissolved in water per liter of latex followed by 70 mL of HFC-4310 (1,1,1,2,3,4,4,5,5,5-decafluoropentane) per liter of latex with rapid stirring. The filter cake was washed with water and dried in an air oven at 90-100°C.

TABLE 8

Monomer Precharge TFE/VF/HFP (wt%)	Monomer Make-up TFE/VF/HFP (wt%)	Monomer Fed (g)	Polymer Comp. Solids (wt%)	Polymer (g)	TFE/VF/HFP (wt%)
15/3/82		750.9	2.1	96.6	38.3/42.8/19
9/3/88	29/46/25	1702	18.3	1063	26.2/46.4/27.5
10/10/80		636.1	2.2	99.7	20.3/57.8/22

Poly(VF/TFE/HFP) samples of different VF content, see Table 9 below, were used for the primer coat. Solutions, 2 wt % poly(VF/TFE/HFP) in acetone, were made by agitating chunks of the polymer with solvent for several days at room temperature. PMMA plates measuring 2.5 cm by 5.0 cm by 3 mm thick were used for testing. The PMMA plates were coated by lowering the plates into the polymer solution at a rate of 300 mm/min. and then, immediately, raising the plates back out of the solution at 50 mm/min. After 5-10 minutes air drying, the plates were dried horizontally for 60 minutes in a 100°C air oven.

The topcoat, in every instance the same 57 mole % TFE/43 mole % HFP polymer, was prepared by the same method.

Table 9 below lists Examples in order of increasing VF content.

TABLE 9

Two Coats, VF/TFE/HFP Primer, on PMMA

Comp. #1	Primer Coat Mole %'s VF/TFE/HFP	Adhesion (/100)	Transmittance (%)
Uncoated PMMA control		---	92.1
Example #29	42.8/38.3/19.0	99	96.3
Example #30	46.4/26.2/27.5	100	97.3
Example #31	57.8/20.8/22.0	100	96.0

For VF contents from about 42 to 58 mole %, use of poly(VF/TFE/HFP) as the primer coat gives excellent transmittance (>96.0%) relative to uncoated PMMA (92.1%) along with excellent adhesion (>99/100).

#### EXAMPLE 32

Two Coats on PMMA

Use of Graft of TFE to PVOH as Primer Coat

A poly(vinyl alcohol) to which 46 mole % TFE had been grafted (PVOH-g-TFE) was used for the primer coat. A solution, 2 wt % in acetone, was made by agitating chunks of the polymer with solvent for several days at room temperature. PMMA plates measuring 2.5 cm by 5.0 cm by 3 mm thick were

used for testing. The PMMA plates were coated by lowering the plates into the polymer solution at a rate of 300 mm/min. and then, immediately, raising the plates back out of the solution at 50 mm/min. After 5-10 minutes air drying, the plates were dried horizontally for 60 minutes in a 100°C air oven.

5        The topcoat, an 57 mole % TFE/43 mole % HFP polymer, was prepared by the same method.

Table 10 below gives adhesion and transmission results.

**TABLE 10**

Two Coats, PVOH-g-TFE Primer, on PMMA

	Primer Coat PVOH-g-TFE	Adhesion (/100)	Transmittance (%)
Comp. #1	Uncoated PMMA control	--	92.1
Example #32	46 mole % TFE	97	97.1

10        Use of poly(PVOH-g-TFE) as the primer coat gave excellent transmittance (97.1%) relative to uncoated PMMA (92.1%) along with excellent adhesion (97/100).

**EXAMPLE 33**

**COMPARATIVE EXAMPLES 15-16**

15        One Coat Poly(VF<sub>2</sub>/TFE/HFP) on PET

Coatings were prepared as in Examples 1 to 9. PET sheets measuring 2.5 by 5.0 cm by 0.12 mm thick were used as substrate. Transmittance and adhesion were measured with the results shown in the table below which lists Examples and Comparative Examples.

20

**TABLE 11**

Poly(VF<sub>2</sub>/TFE/HFP) Coat on PET

	Mole %'s VF <sub>2</sub> /TFE/HFP	Adhesion (/100)	Transmittance (%)
Comp. #15	Uncoated PET control	--	85.0
Comp. #16	0/57/43	2	96.0
Example #33	18.7/43.3/38.0	99	96.0

Uncoated PET showed 85.0% transmission. Simultaneous good adhesion (>99/100) and improved transmission (>96%) relative to uncoated PET were observed.



EXAMPLE 34COMPARATIVE EXAMPLE 17-18

One Coat Poly(VF<sub>2</sub>/TFE/HFP) on Polysulfone

Coatings were prepared as in Example 1 to 9. Polysulfone sheets measuring 2.5 X 5.0 cm by 0.05 mm thick were as substrate. Transmittance and adhesion results are shown in the table below which lists Examples and Comparative Examples.

TABLE 12

Single Coat Poly(VF<sub>2</sub>/TFE/HFP) on Polysulfone

	Mole %'s VF <sub>2</sub> /TFE/HFP	Adhesion (/100)	Transmittance (%)
Comp. #17	Uncoated PS	--	88.5
Comp. #18	0/57/43	97	98.2
Example #34	18.7/43.3/38.0	100	95.0

Uncoated polysulfone showed 88.5% transmittance. Simultaneous good adhesion (>97/100) and improved transmission (>95%) relative to uncoated polysulfone (88.5%) were observed.

EXAMPLE 35COMPARATIVE EXAMPLE 19

Two coat polymer films were prepared on PMMA sheet as in Examples 15-18. A Teflon<sup>®</sup> AF top coat was used. Transmittance and adhesion were measured with the results shown in the table below which lists the Examples and Comparative Examples.

TABLE 13

Two Coats, Poly(VF<sub>2</sub>/TFE/HFP) and Teflon<sup>®</sup> AF, on PMMA

	Mole %'s VF <sub>2</sub> /TFE/HFP	Adhesion (/100)	Transmittance (%)
Comp. #1	Uncoated PMMA control	--	92.1
Comp. #19	AF1600 control (no lower coat)	0	98.1
Example #35	49.3/27.7/23.0	100	98.0

Adhesion was 100/100 for the two coat sheet (VF<sub>2</sub>/TFE/HFP and Teflon<sup>®</sup> AF) but only 0/100 for the sheet with a single coating of Teflon<sup>®</sup> AF. This shows that poly(VF<sub>2</sub>/TFE/HFP) is an effective primer that further improves the adhesion of Teflon<sup>®</sup> AF.

Transmittance at 500 nm was 98.0% for two coat sheet (VF<sub>2</sub>/TFE/HFP and AF) but only 92.1 for uncoated PMMA control. This shows that Teflon<sup>®</sup> AF

is an effective top coat that further improves the transmittance of poly(VF<sub>2</sub>/TFE/HFP).

#### EXAMPLES 36-45

Aqueous Polymerization of VAc/TFE/HFIB. A 1-L stirred vertical  
5 autoclave was charged with a solution of 0.3 g of Plasdone K-90 (steric stabilizer)  
and 5 mL isopropanol (chain transfer agent) in 400 mL of deionized water. Vinyl  
acetate (126 g, 1.47 mole) and 0.6 g of Vazo<sup>®</sup> 52 were added. The vessel was  
closed, pressurized to 100 psi with nitrogen and vented twice. The vessel was  
pressured to 295 psi with nitrogen as a leak test and vented. The vessel was  
10 cooled to about -4°C, evacuated and charged with 42 g (0.26 mol) of  
hexafluoroisobutylene and 42 g (0.42 mol) of tetrafluoroethylene. With stirring at  
750 rpm, the vessel contents were heated to 70°C and maintained for 3 hr. The  
contents was heated to 85°C and maintained for 3 hr. After cooling to room  
temperature and venting to atmospheric pressure, the aqueous suspension was  
15 removed from the vessel using water as necessary to rinse. An additional 350 mL  
of deionized water were added and the white suspension was heated with stirring  
on a hot plate until about 250 mL of solution had evaporated. After cooling to  
room temperature, the solid was easily filtered on a sintered glass funnel and  
washed with deionized water. It was dried in a vacuum oven at 90°C overnight  
20 giving 181.8 g (87%) of white polymer.

Nonaqueous Polymerization of VAc/TFE/HFIB. A 1-L stirred vertical  
autoclave was charged with a solution of 126 g of vinyl acetate in 110 g of methyl  
acetate and 200 g of tert-butanol. The vessel was closed, pressurized to 100 psi  
with nitrogen and vented twice. The vessel was pressured to 295 psi with  
25 nitrogen as a leak test and vented. The vessel was cooled to about -4°C,  
evacuated and charged with 63 g of tetrafluoroethylene and 21 g of HFIB. With  
stirring at 750 rpm, the vessel contents were heated to 70°C. A solution (25 mL)  
of 0.2 g Vazo<sup>®</sup> 52 in 25 mL methyl acetate was injected at 5 ml/min. After 3 hr.  
the vessel contents were allowed to cool to room temperature and the remaining  
30 gases were vented. The viscous solution was removed from the vessel by suction,  
diluting with acetone as necessary to lower solution viscosity. The polymer  
solution, further diluted with acetone if necessary to give a clear solution, was  
added slowly in 30-45 mL portions to 16 oz of deionized water and a small  
amount of ice in a blender. The precipitated solid was filtered in a sintered glass  
35 funnel. After all polymer had been precipitated the combined solids were washed  
in portions with water, filtered and pressed with a rubber dam. The solid was  
dried for several hours in a vacuum oven with a slow nitrogen purge at  
110-115°C. The resulting white solid weighed 141.1 g (67%).

Table 14 below gives results for polymerizations carried out by one of the methods listed above.

Vinyl acetate content was determined by hydrolysis of the acetate groups using excess of sodium hydroxide in refluxing THF, followed by titration of  
5 excess base by standard hydrochloric acid solution. GPC analyses were conducted using THF as solvent and polystyrene standards. Elemental analyses were done by Schwarkkoff Microanalytical Laboratory.  $^{19}\text{F}$  NMR spectra were generally measured in THF- $d_6$  solutions using TMS and CFC-11 as internal  
10 standards.  $^{19}\text{F}$  NMR was used to assign relative amounts of the two fluorinated monomers from integration of the  $\text{CF}_3$  groups of HFIB at -66 to -70 versus the  $\text{CF}_2$  groups from TFE at -110 to -126.

TABLE 14

Ex.	Monomers (g)	Weight Ratio Feed/(Product <sup>a</sup> )	Polym. Solv. b	Reactor	Yield, g (%)	Wt. % VAc	F NMR (mole %)	Refractive Index	Inh. Visc.	% Fc	GPC Mw/Mn/PD
36	VAc (52) TFE (30) HFIB (49)	40:23:37 (39:13:48)	t-BuOH MeAc	400 mL	94.6 (72)	39.0	TFE 31% HFIB 69%	1.4111	0.41	38.92	148,000 84,900 1.75
37	VAc (86) TFE (50) HFIB (82)	39:23:38 (36:12:52)	Water PVP	1 L	175.6 (81)	35.5	TFE 28% HFIB 72%	1.4169	0.38	36.70	177,000 82,500 2.15
38	VAc (103) TFE (40) HFIB (66)	49:19:32 (50:12:38)	Water PVP	1 L	182.5 (87)	50.2	TFE 33% HFIB 67%	1.4191	0.52	31.09	252,000 81,800 3.08
39	VAc (126) TFE (42) HFIB (42)	60:20:20 (58:16:26)	Water PVP	1 L	181.8 (87)	58.1	TFE 50% HFIB 50%	1.4307	0.79	22.95	349,000 120,000 2.90
40	VAc (126) TFE (63) HFIB (21)	60:30:10 (69:19:12)	Water <sup>d</sup> PVP	1 L	172.9 (82)	68.6	TFE 73% HFIB 27%	1.4368	1.98	20.83	786,000 208,000 3.77
41	VAc (147) TFE (42) HFIB (21)	70:20:10 (71:16:13)	Water <sup>d</sup> PVP	1 L	186.3 (89)	70.7	TFE 66% HFIB 34%	1.4439	2.01	17.69	857,000 243,000 3.52
42	VAc (126) TFE (63) HFIB (21)	60:30:10 (62:24:14)	t-BuOH MeAc	1 L	141.1 (67)	61.5	TFE 74% HFIB 26%	1.4284	0.78	26.22	235,000 100,000 2.33
43	VAc (126) TFE (42) HFIB (42)	60:20:20 (57:15:27)	t-BuOH MeAc	1 L	148.4 (71)	57.2	TFE 48% HFIB 52%	1.4198	0.59	29.83	204,000 116,000 1.76

Ex.	Monomers (g)	Weight Ratio Feed/(Product <sup>a</sup> )	Polym. Solv. <sup>b</sup>	Reactor	Yield, g (%)	Wt. % VAc	F NMR (mole %)	Refractive Index	Inh. Visc.	% F <sup>c</sup>	GPC Mw/ Mn/PDI
44	VAc (147)	70:20:10 (66:19:15)	t-BuOH	1 L	142.5 (68)	66	TFE 68% HFIB 32%	1.4353	0.78	22.33	230,000 126,000 1.82
	TFE (42)		MeAc								
	HFIB (21)										
45	VAc (147)	70:20:10 (69:17:14)	Water	1 L	187.1 (89)	68.8	TFE 68% HFIB 32%	1.4422	1.09	17.83	437,000 145,000 3.0
	TFE (42)		PVP								
	HFIB (21)										

<sup>a</sup> Vinyl acetate content determined by hydrolysis of the acetate groups using standard base, fluoromonomer incorporation was determined by <sup>19</sup>F NMR. <sup>b</sup> Polyvinyl pyrrolidone (0.3 g) used as dispersing agent and isopropanol (5 mL) used as chain transfer agent in aqueous polymerizations. <sup>c</sup> Elemental analysis <sup>d</sup> No chain transfer agent used.

EXAMPLES 46-48

## Two Coats on PMMA

## Use of Poly(VAc/TFE/HFIB) as Primer Coat

## Preferred VAc Content

5 Poly(VAc/TFE/HFIB) samples of different VAc content, see Table 9 below, were used for the primer coat. Solutions, 2 wt % poly(VAc/TFE/HFIB) in acetone, were made by agitating chunks of the polymer with solvent for several days at room temperature. PMMA plates measuring 2.5 cm by 5.0 cm by 3 mm thick were used for testing. The PMMA plates were coated by lowering the plates  
10 into the polymer solution at a rate of 300 mm/min. and then, immediately, raising the plates back out of the solution at 50 mm/min. After 5-10 minutes air drying, the plates were dried horizontally for 60 minutes in a 100°C air oven.

The topcoat, in every instance the same 57 mole % TFE/43 mole % HFP polymer, was prepared by the same method.

15 Table 15 below lists Examples and in order of increasing VAc content.

TABLE 15

Two Coats, VAc/TFE/HFIB Primer, on PMMA

	Primer Coat Mole % VAc/TFE/HFIB	Adhesion (/100)	Transmittance (%)
Comp. #1	Uncoated PMMA control	---	92.1
Example #46	36/12/52	100	96.8
Example #47	58/16/26	100	97.6
Example #48	69/17/14	100	97.3

For VAc contents from about 36 to 69 mole %, use of  
poly(VAc/TFE/HFIB) as the primer coat gives excellent transmittance (>96.8%)  
20 relative to uncoated PMMA (92.1%) along with excellent adhesion (100/100).

What is claimed is:

1. A one layer coating system for coating a substrate comprising a fluorinated copolymer having the formula

5 VF<sub>2</sub>/TFE/HFP

wherein the molar ratio of TFE to HFP is between 0.9 and 1.9 and the VF<sub>2</sub> content is about 12-40%.

2. The coating system of Claim 1 wherein the VF<sub>2</sub> content is 12 to  
10 40 mole % and the substrate is PMMA.

3. The coating system of Claim 1 wherein the VF<sub>2</sub> content is 18 to 40 mole % and the substrate is selected from the group consisting of PC, PET, and PS.

4. The coating of Claim 1 wherein the thickness of the coating is  
15 between 10 nm and 1000 nm.

5. The coating of Claim 4 wherein the thickness of the coating is between 70 nm and 120 nm.

6. A two-layer coating system for coating substrates selected from the group consisting of PMMA, PC, PET, and PS comprising an upper layer selected  
20 from the group consisting of:

a) poly(TFE/HFP) and poly(VF<sub>2</sub>/TFE/HFP), wherein the molar ratio of HFP to TFE is between about 0.9 and 1.9 and, in the case of the VF<sub>2</sub>/TFE/HFP terpolymer, the concentration of VF<sub>2</sub> is about 19 mole %; and

b) poly(TFE/perfluoro-2,2-dimethyldioxole) wherein the  
25 concentration of the perfluorodimethyldioxole is between 60 and 90 mole %; and a lower coating layer selected from the group consisting of:

a) poly(VF<sub>2</sub>/TFE/HFP) wherein the ratio of TFE to HFP is between about 0.9 and 1.9 and the concentration of VF<sub>2</sub> is between about 18 and 60% on PMMA substrates and between about 12 and 40 mole % on PC, PET, and PS  
30 substrates;

b) poly(VF/TFE/HFP) wherein the ratio of TFE to HFP is between about 2.1 and 0.9 and the concentration of VF is between about 42 and 58 mole %;

c) poly(VAc/TFE/HFIB) wherein the concentration of VAc is  
35 between 36 and 69 mole % and the concentration of HFIB is between 14 and 52 mole %; and

d) TFE graft to PVOH wherein about 46 mole % TFE has been grafted to the PVOH.

7. The two layer coating system of Claim 6 wherein the thickness of the lower coating layer is less than 20 nm.

8. The two layer coating system wherein the thickness of the upper layer is 10 nm to 1000 nm.

5 9. The two layer coating system of Claim 8 wherein the thickness of the upper layer is between 70 nm and 120 nm.

10. A composition prepared by the polymerization of vinyl acetate (VAc,  $\text{CH}_3\text{-C(O)-OCH=CH}_2$ ), tetrafluoroethylene ( $\text{CF}_2=\text{CF}_2$ ), and hexafluoroisobutylene ( $((\text{CF}_3)_2\text{C=CH}_2)$ ).

10



(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
21 September 2000 (21.09.2000)

PCT

(10) International Publication Number  
**WO 00/55130 A3**

(51) International Patent Classification<sup>7</sup>: **C09D 127/12**,  
C08J 7/04, B05D 7/26, C08F 214/26, 218/08

Takahasi [JP/JP]; Pepaminto Haitzu A27, 1-3-2 Mat-  
sugasaki, Yonezawa-shi, Yamagata (JP). **USCHOLD**,  
Ronald, Earl [US/US]; 1104 Dorset Drive, West Chester,  
PA 19382 (US). **WHELAND**, Robert, Clayton [US/US];  
510 Twaddell Mill Road, Wilmington, DE 19807 (US).

(21) International Application Number: **PCT/US00/07263**

(22) International Filing Date: 15 March 2000 (15.03.2000)

(74) Agent: **SIEGELL**, Barbara, C.; E.I. du Pont de Nemours  
and Company, Legal Patent Records Center, 1007 Market  
Street, Wilmington, DE 19898 (US).

(25) Filing Language: English

(26) Publication Language: English

(81) Designated States (*national*): CA, JP, KR, US.

(30) Priority Data:  
60/124,520 16 March 1999 (16.03.1999) US

(84) Designated States (*regional*): European patent (AT, BE,  
CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC,  
NL, PT, SE).

(71) Applicant (*for all designated States except US*): **E.I. DU  
PONT DE NEMOURS AND COMPANY** [US/US]; 1007  
Market Street, Wilmington, DE 19898 (US).

Published:  
— *With international search report.*

(72) Inventors; and

(88) Date of publication of the international search report:  
12 April 2001

(75) Inventors/Applicants (*for US only*): **FEIRING**, Andrew,  
Edward [US/US]; 7 Buckridge Drive, Wilmington, DE  
19807 (US). **IWATO**, Satoko [JP/JP]; 4-27-8, Jingumae,  
Shibuya-ku, Tokyo (JP). **KAKU**, Mureo [JP/JP]; 2-32-2,  
Toyosatodai Utsunomiya, Tochigi (JP). **TATSUHIRO**,

*For two-letter codes and other abbreviations, refer to the "Guid-  
ance Notes on Codes and Abbreviations" appearing at the begin-  
ning of each regular issue of the PCT Gazette.*



**WO 00/55130 A3**

(54) Title: **FLUOROPOLYMER LOW REFLECTING LAYERS FOR PLASTIC LENSES AND DEVICES**

(57) Abstract: A one or two layer coating system has been developed for plastic substrates. The one coating system low reflect-  
ing layer consists of VF<sub>2</sub>/TFE/HFP. In the two coating system is the upper coating layer consists of TFE/HFP, VF<sub>2</sub>/TFE/HFP, or  
TFE/Perfluorodioxole, and the lower coating layer consists of VF<sub>2</sub>/TFE/HFP, VF/TFE/HFP, VAc/TFE/HFIB, or TFE graft to PVOH.  
A new fluoropolymer composition was prepared for use in the coating systems, prepared by the copolymerization of vinyl acetate,  
tetrafluoroethylene, and hexafluoroisobutylene.

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 00/07263

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C09D127/12 C08J7/04 B05D7/26 C08F214/26 C08F218/08

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09D C08J C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, CHEM ABS Data, WPI Data

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 798 158 A (KOIKE MASAKI ET AL) 25 August 1998 (1998-08-25) claims 1,5 ---	1
X	EP 0 050 436 A (DU PONT) 28 April 1982 (1982-04-28) claims 1-4; example 24 ---	1
X	EP 0 889 066 A (DU PONT) 7 January 1999 (1999-01-07) claims; example 89 ---	1
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

31 October 2000

Date of mailing of the international search report

14.12.2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Friederich, P

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 00/07263

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	<p>DATABASE WPI  Section Ch, Week 199632  Derwent Publications Ltd., London, GB;  Class A14, AN 1996-317814  XP002151596  &amp; JP 08 142280 A (FUKUBI KAGAKU KOGYO KK),  4 June 1996 (1996-06-04)  abstract</p> <p>---</p>	8,9
A	<p>DATABASE WPI  Section Ch, Week 199724  Derwent Publications Ltd., London, GB;  Class A14, AN 1997-268591  XP002151597  &amp; JP 09 096701 A (NIKON CORP),  8 April 1997 (1997-04-08)  abstract</p> <p>---</p>	6,7
A	<p>US 5 132 164 A (MORIYA YOSHIHISA ET AL)  21 July 1992 (1992-07-21)  the whole document</p> <p>---</p>	6-9
A	<p>WO 97 01599 A (DU PONT)  16 January 1997 (1997-01-16)  the whole document</p> <p>---</p>	6-9
A	<p>US 5 053 470 A (WU CHENGJIU)  1 October 1991 (1991-10-01)  the whole document</p> <p>---</p>	10
A	<p>US 5 880 234 A (AKAMA SHUYO ET AL)  9 March 1999 (1999-03-09)  the whole document</p> <p>-----</p>	10

# INTERNATIONAL SEARCH REPORT

International application No.  
PCT/US 00/07263

## Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:  
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☐ Claims Nos.:  
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
3. ☐ Claims Nos.:  
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

## Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

see additional sheet

1. ☒ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

### Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☒ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

This International Searching Authority found multiple (groups of) inventions in this international application, as follows:

1. Claims: 1-5

One layer coating comprising terpolymer of VF<sub>2</sub>/TFE/HFP with the molar ratio of TFE to HFP between 0.9-1.9 and VF<sub>2</sub> being 12-40%

2. Claims: 6-7

Two layer coating comprising terpolymer of VF<sub>2</sub>/TFE/HFP with the molar ratio of HFP to TFE between 0.9-1.9 and VF<sub>2</sub> being 12-40%

3. Claims: 8-9

Two layer coating having specific thickness without taking reference to coating composition of claim 6-7 nore 1-5

4. Claim : 10

Composition prepared by polymerisation of vinyl acetate, tetraethylene and hexafluoroisobutylene.

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 00/07263

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5798158	A	25-08-1998	JP 8118549 A	14-05-1996
			US 6037062 A	14-03-2000
EP 0050436	A	28-04-1982	US 4329399 A	11-05-1982
			CA 1157714 A	29-11-1983
			DE 3174323 D	15-05-1986
			JP 1013425 B	06-03-1989
			JP 1526664 C	30-10-1989
			JP 57091263 A	07-06-1982
EP 0889066	A	07-01-1999	US 5478905 A	26-12-1995
			US 5663255 A	02-09-1997
			EP 0891994 A	20-01-1999
			EP 0889028 A	07-01-1999
			EP 0889067 A	07-01-1999
			CN 1173882 A	18-02-1998
			EP 0808335 A	26-11-1997
			JP 11501685 T	09-02-1999
			WO 9624624 A	15-08-1996
			US 5637663 A	10-06-1997
			US 6133389 A	17-10-2000
JP 8142280	A	04-06-1996	JP 3007007 B	07-02-2000
JP 9096701	A	08-04-1997	NONE	
US 5132164	A	21-07-1992	JP 2151436 A	11-06-1990
			JP 2739976 B	15-04-1998
			US 5256472 A	26-10-1993
WO 9701599	A	16-01-1997	US 5726247 A	10-03-1998
			AU 6482396 A	30-01-1997
			EP 0837901 A	29-04-1998
			JP 2000500161 T	11-01-2000
			US 5264247 A	23-11-1993
US 5053470	A	01-10-1991	NONE	
US 5880234	A	09-03-1999	JP 10053623 A	24-02-1998